

UNCLASSIFIED



BMI-745

Subject Category: METALLURGY AND CERAMICS

UNITED STATES ATOMIC ENERGY COMMISSION

THERMAL CONDUCTIVITY OF POWDER-
METALLURGY URANIUM


By
H. W. Deem
H. R. Nelson



May 21, 1952

Battelle Memorial Institute
Columbus, Ohio

Technical Information Service, Oak Ridge, Tennessee



DTIC QUALITY INSPECTED 8

UNCLASSIFIED

19950814 115

X-18014

Date Declassified: November 30, 1955.

This report was prepared as a scientific account of Government-sponsored work and is made available without review or examination by the Government. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights. The Commission assumes no liability with respect to the use of, or for damages resulting with respect to the use of any information, apparatus, method, or process disclosed in this report.

This report has been reproduced directly from the best available copy.

Issuance of this document does not constitute authority for declassification of classified material of the same or similar content and title by the same authors.

Since nontechnical and nonessential prefatory material has been deleted, the first page of the report is page 7.

Printed in USA, Price 15 cents. Available from the Office of Technical Services, Department of Commerce, Washington 25, D. C.

THERMAL CONDUCTIVITY OF POWDER-METALLURGY URANIUM

by

H. W. Deem and H. R. Nelson

May 21, 1952

ABSTRACT

Thermal-conductivity measurements were made on three powder compacts of uranium and, for comparison, on one sample of cast-and-wrought metal. The conductivities of all specimens ranged from 0.23₄ to 0.24₉ watt cm⁻¹C⁻¹ at 40°C and from 0.25₀ to 0.26₂ watt cm⁻¹C⁻¹ at 100°C. The slight differences in conductivity probably can be attributed to differences in density.

BATTELLE MEMORIAL INSTITUTE
505 King Avenue
Columbus 1, Ohio

-7-

Accession For	
NTIS GRANT	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Avail and/or	
Spec	Special

A-1

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	9
APPARATUS AND METHOD	9
SPECIMENS	11
CALCULATIONS	11
RESULTS.	12
REFERENCES	15

INTRODUCTION

Thermal-conductivity measurements were made on three uranium powder compacts and one specimen of conventionally cast and rolled uranium metal. The powder-metallurgy specimens were prepared by Sylvania Electric Products Corporation, and the conductivity measurements were carried out at the request of Sylvania to determine possible differences between conventional and powder-metallurgy materials.


APPARATUS AND METHOD

The method used is a modified form of that described by Van Dusen and Shelton⁽¹⁾. It consists of introducing heat, at a constant rate, into a standard heat-flow meter, one end of which is in series with the specimen. Heat is removed at a constant rate from the other end of the specimen by circulating water at a constant flow rate and temperature. Temperature gradients measured along standard and specimen permit calculating the quantity of heat flowing and the thermal conductivity of the specimen.

Figure 1 is a schematic diagram of the apparatus. An Armco iron standard heat-flow meter, H, 2 cm in diameter and 15 cm long, was tin soldered at its lower end to a heater, I, and at its upper end to the specimen, D. The specimen, 2 cm in diameter and 5 cm long, was tin soldered at its upper end to a water-cooled cap, A. The relative positions and lengths of the specimen and the Armco standard were interchanged for this work, as compared with their usual positions. This arrangement permitted operation at lower specimen temperatures with less oxidation than with the customary assembly.

It was difficult to get tin to adhere to the uranium. The method finally used was to plate the specimen ends with about 0.001 inch of silver, followed by about 0.003 inch of nickel plated on the silver, and then, another layer of silver about 0.0002 inch thick plated on the nickel. Appropriate chemical and anodic pickles were employed to get clean surfaces. A tin-solder joint made with this plated surface was not completely satisfactory because the plating sometimes separated from the uranium.

Specimen and standard are surrounded by a guard cylinder, O and P, while the entire assembly is in an enclosing can, Q. Dried Sil-O-Cel



- | | |
|--------------------------|-------------------------|
| A - Cooling Plate | K - Guard Heater |
| B - Cooling Tube | L - Air Cooling Coils |
| C - Transite | M - Inconel Tubes |
| D - Specimen | N - Supports |
| E - Ring Heater | O - Inconel Guard Tube |
| F - Heater Leads | P - Nickel Guard Tube |
| G - Thermal Insulation | Q - Steel Container |
| H - Standard | R - Alundum Disk |
| I - Inconel Heater Block | S - Inconel Bottom |
| J - Main Heater | Numbers - Thermocouples |

FIGURE 1. DIAGRAMMATIC SKETCH OF APPARATUS USED FOR
THERMAL-CONDUCTIVITY MEASUREMENTS

0-7226

insulation fills the spaces and serves to reduce radial heat flow. Purified argon introduced through the can bottom at M was used to protect the uranium from oxidation.

Heat is supplied to the Armco iron standard and specimen by a resistance heater, J. Similar resistance heaters, K and L, supply heat to the guard cylinder. All heaters are powered from a voltage-regulated source to insure a steady heat input.

Temperature was measured at 3 places on the Armco standard, 3 places on the specimen, and 5 places on the guard cylinder. Thermocouples made from 36-gage Chromel-Alumel calibrated wire are wedged into small holes drilled in the specimen and standard. In operation, heat is supplied to the specimen-standard assembly to bring the specimen to the desired mean temperature. Heat also is supplied to the guard cylinder to bring its temperature as nearly as possible to that of the specimen and standard at corresponding levels. Supplementary cooling coils, L and B, in Figure 1 are provided on the guard cylinder, permitting the use of air or water to aid in matching temperatures. After an equilibrium is established and a good temperature balance exists between the specimen and standard with the guard, thermocouple readings are recorded using a Type K Leeds and Northrup potentiometer.

SPECIMENS

Three powder-compact specimens were furnished by Sylvania. Two were prepared by hot pressing uranium hydride, UH_3 , and one was prepared by hot pressing metal powder. For comparison purposes, a sample of pile-grade, alpha-rolled metal was measured. Table 1 gives other information concerning the specimens.

CALCULATIONS

Temperatures for determining the temperature gradients were taken only after steady heat flow was established and radial temperature gradients were minimized. Under these conditions, the rates of heat flow in standard and specimen are identical and may be equated,

$$q = \frac{K_s A_s (\Delta T)_s}{X_s} = \frac{K_I A_I (\Delta T)_I}{X_I}$$

The desired thermal conductivity then may be expressed in terms of the known conductivity of the standard and the readily measured temperature gradients,

$$K_s = \frac{X_s K_I A_I (\Delta T)_I}{A_s X_I (\Delta T)_s}$$

where,

- q = rate of heat flow, watts
- K_s = thermal conductivity of specimen, watts $\text{cm}^{-1}\text{C}^{-1}$
- K_I = thermal conductivity of standard, watts $\text{cm}^{-1}\text{C}^{-1}$
- A_s = cross-sectional area of specimen, cm^2
- A_I = cross-sectional area of standard, cm^2
- X_s = distance between thermocouple beads on specimen, cm
- X_I = distance between thermocouple beads on standard, cm
- $(\Delta T)_s$ = temperature drop across X_s , degree C
- $(\Delta T)_I$ = temperature drop across X_I , degree C

RESULTS

Figure 2 is a plot of specimen thermal conductivity vs. mean specimen temperature. Two equilibria were obtained for each specimen and a straight line drawn through the points.

Table 1 lists thermal-conductivity values at 40 C and 100 C, as taken from Figure 2. Thermal conductivities of the compacts appear to increase with density, as would be expected. The differences, however, are small and are probably just barely significant as comparative values.

Thermal-conductivity values for uranium given in the literature differ widely. A Canadian⁽²⁾ report shows thermal-conductivity values for uranium at about 100 C from 0.246 to 0.273 watt $\text{cm}^{-1}\text{C}^{-1}$, with an average value of 0.260 watt $\text{cm}^{-1}\text{C}^{-1}$. A British⁽³⁾ report shows conductivities from 0.176 to 0.201 watt $\text{cm}^{-1}\text{C}^{-1}$ for uranium with densities from 14.8 to 18.5 g/cm^3 . An extrapolated thermal conductivity for a density of 19.0 g/cm^3 is 0.222 watt $\text{cm}^{-1}\text{C}^{-1}$ at 60 C.

A mean density value for alpha-extruded uranium with a reduction ratio of 8.1 is $18.942 \pm .001 \text{ g}/\text{cm}^3$ at 25 C, according to an MIT report⁽⁴⁾.

TABLE 1. URANIUM THERMAL CONDUCTIVITY

Specimen Number	Original Specimen Stock		Specimen Density (From Volume and Weight), g/cm ³	Thermal Conductivity, watt cm ⁻¹ C ⁻¹	
	Diameter, inches	Length, inches		at 40 C	at 100 C
688(1)	1.449	1.98	18.84 ⁽⁵⁾	0.234	0.250
690(2)	1.445	2.06	18.90 ⁽⁵⁾	0.247	0.259
695(3)	1.445	2.008	18.86 ⁽⁵⁾	0.236	0.255
BMI(4)	Rough Forging		18.86 ⁽⁶⁾	0.249	0.262

(1) Compact prepared by decomposition of UH₃ under hot pressing. Grain size 1/4- to 1/2-mm-diameter. Coarse grain resulted from overheating.

(2) Same as Specimen 688, except fine grained. Grain size not checked but thought to be 10- to 20-micron diameter.

(3) Hot-pressed U powder compact.

(4) U metal treated, prior to machining specimen, as follows:

(a) Rolled from 1-5/8-inch to 7/8-inch-diameter at 500 C.

(b) Heat treated for 1/2 hour at 725 C (in furnace during heating cycle).

(c) Water quench from 725 C.

(d) Alpha anneal, 1 hour at 525 C (furnace cooled).

(5) Densities as calculated by Sylvania from volume and weight of pieces before specimen cylinders were machined.

(6) Density as calculated from specimen weight and volume after run. This value thought to be low because of some specimen dimensional irregularity, with a consequent error in its volume measurement. Correct density probably near 18.94 g/cm³.




FIGURE 2. THERMAL CONDUCTIVITY OF URANIUM POWDER-METALLURGY COMPACTS
A-1914

REFERENCES

- (1) Van Dusen, M. S., and Shelton, S. M., "Apparatus for Measuring Thermal Conductivity of Metals up to 600 C", National Bureau of Standards (U. S.), Research Paper V 12 (No. 668), 1934, pages 429-440.
- (2) CRR-438 (SECRET), "Thermal Conductivity of Metals at High Temperatures, II Thermal Conductivity of Uranium: A Preliminary Study", National Research Council of Canada, Atomic Energy Project, Ottawa, Ontario, December 16, 1949.
- (3) BR-280A, "Remarks on Some Physical Properties of Uranium Metal", Clarendon Laboratory, Oxford, England; reproduced by US-AEC Technical Information Division ORE, Oak Ridge, Tennessee, April 25, 1950.
- (4) MIT-1029 (Part II) (SECRET), MIT Metallurgical Project, Technical Progress Report for the period January through June, 1949; issued September 16, 1949, Massachusetts Institute of Technology, Cambridge, Massachusetts.